

IMITACIÓN CERA DE ABEJAS PARA VELAS

FICHA TÉCNICA

Test Method	Units	Method	Specification	Result
Congeaing Point	°C	ASTM D938	70 - 75	74
Needle Penetration25°C	1/10 mm	ASTM D1321	Max 30	29
Viscosity 100°C	mm ² /s	ASTM D445	12 - 18	16
Colour ASTM		ASTM D 1500	Max 1,5	1,4
Oil content	%	ASTM D 723	Max 2.5	1.9